

Technical features						
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results	Reference standard
			N ≥ 15 cm			
			(%)	(mm)	MATTE	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%	ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%	
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%	
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%	
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,20%	
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant	
	Water absorption, percent mass fraction	≤ 0,5%			Average value 0,08%	ISO 10545-3
	Breaking strength in N (thickness < 7.5 mm)	≥ 700			Average value 1350 N	ISO 10545-4
	Bending strength in N/mm ²	≥ 35			Average value 52 N/mm ²	
	Resistance to deep abrasion	≤ 175 mm ³			Average value 140 mm ³	ISO 10545-6
	Thermal shock resistance	Available testing method			Resistant	ISO 10545-9
	Resistance to staining	Available testing method			Class 4	ISO 10545-14
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration			LB	ISO 10545-13
	Resistance to household chemicals and swimming pool salts	Minimum class B			A	
	Frost resistance	Required			Resistant	ISO 10545-12
	Release of hazardous substances	Declared value for GL surfaces intended for countertop applications			Compliant	DM 1-2-2007 Reg. CE 1935-2004
	Dynamic coefficient of friction	See manufacturer's declaration			≥ 0,42 wet	ANSI-A326.3
	Shod ramp slipperiness	See manufacturer's declaration			R9 (6° < α ≤ 10°)	DIN EN 16165 ANNEX B

Technical features						
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results	Reference standard
			N ≥ 15 cm			
			(%)	(mm)	MATTE	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%	ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%	
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%	
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%	
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,35%	
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant	
	Water absorption, percent mass fraction	≤ 0,5%			Average value 0,08%	ISO 10545-3
	Breaking strength in N (thickness < 7.5 mm)	≥ 1300			Average value 2200 N	ISO 10545-4
	Bending strength in N/mm ²	≥ 35			Average value 50 N/mm ²	
	Resistance to deep abrasion	≤ 175 mm ³			Average value 140 mm ³	ISO 10545-6
	Thermal shock resistance	Available testing method			Resistant	ISO 10545-9
	Resistance to staining	Available testing method			Class 4	ISO 10545-14
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration			LA	ISO 10545-13
	Resistance to high concentrations of acids and alkali	Available testing method			HA	
	Resistance to household chemicals and swimming pool salts	Minimum class B			A	
	Frost resistance	Required			Resistant	ISO 10545-12
	Dynamic coefficient of friction	See manufacturer's declaration			≥ 0,42 wet	ANSI-A326.3
	Shod ramp slipperiness	See manufacturer's declaration			R9 (6° < α ≤ 10°)	DIN EN 16165 ANNEX B