

Technical features										
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL				Standard requirements		Test results				Reference standard
				N ≥ 15 cm						
						(%)	(mm)	GLOSSY	MATTE SILK	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%				ISO 10545-2	
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%					
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%					
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%					
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,20%					
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant					
	Water absorption, percent mass fraction	≤ 0,5%			Average value 0,08%				ISO 10545-3	
	Breaking strength in N (thickness < 7.5 mm)	≥ 700			Average value 1350 N				ISO 10545-4	
	Bending strength in N/mm ²	≥ 35			Average value 52 N/mm ²					
	Resistance to deep abrasion	≤ 175 mm ³			Average value 140 mm ³				ISO 10545-6	
	Thermal shock resistance	Available testing method			Resistant				ISO 10545-9	
	Resistance to staining	Available testing method			Class 4	Class 5		Class 4	ISO 10545-14	
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration			LB	LA			ISO 10545-13	
	Resistance to household chemicals and swimming pool salts	Minimum class B			A					
	Frost resistance	Required			Resistant				ISO 10545-12	
	Release of hazardous substances	Declared value for GL surfaces intended for countertop applications			Compliant				DM 1-2-2007 Reg. CE 1935-2004	
	Dynamic coefficient of friction	See manufacturer's declaration			-		> 0,40		METODO BCRA	
		See manufacturer's declaration			-		≥ 0,42 wet		ANSI-A326.3	
	Shod ramp slipperiness	See manufacturer's declaration			-			R10 (10° < α ≤ 19°)	DIN EN 16165 ANNEX B	
	Barefoot ramp slipperiness	See manufacturer's declaration			-			Class B (18° ≤ α < 24°)	DIN EN 16165 ANNEX A	
	Pendulum test slipperiness	See manufacturer's declaration			-			PTV > 36 (slider 96)	BS EN 16165 ANNEX C	

Technical features									
Dry-pressed ceramic tiles. Quality specifications, according to control tests of EN 14411-ISO 13006 Appendix G group B1a UGL			Standard requirements		Test results				Reference standard
			N ≥ 15 cm						
			(%)	(mm)	GLOSSY	MATTE SILK	MATTE PTV	GRIP	
	Lenght and with: deviation of the average size for each tile from the work size	Squadrato ISO 13006	± 0,3%	± 1 mm	± 0,15%				ISO 10545-2
	Thickness: deviation of the average thickness of each tile form the work size thickness	Squadrato ISO 13006	± 5%	± 0,5 mm	± 5%				
	Straightness: maximum deviation to the corresponding work sizes	Squadrato ISO 13006	± 0,3%	± 0,8 mm	± 0,10%				
	Orthogonality: permissible deviation in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,3%	± 1,5 mm	± 0,20%				
	Flatness: center curvature, edge curvature, and warpage in relation to the corresponding manufacturing dimensions	Squadrato ISO 13006	± 0,4%	± 1,8 mm	0,35%				
	Surface quality	A minimum of 95% of the tiles are to be free from visible defects			Compliant				
	Water absorption, percent mass fraction	≤ 0,5%		Average value 0,08%				ISO 10545-3	
	Breaking strength in N (thickness < 7.5 mm)	≥ 1300		Average value 2200 N				ISO 10545-4	
	Bending strength in N/mm²	≥ 35		Average value 50 N/mm²					
	Resistance to deep abrasion	≤ 175 mm³		Average value 140 mm³				ISO 10545-6	
	Thermal shock resistance	Available testing method		Resistant				ISO 10545-9	
	Resistance to staining	Available testing method		Class 4				ISO 10545-14	
	Resistance to low concentrations of acids and alkali	See manufacturer's declaration		LB		LA		ISO 10545-13	
	Resistance to high concentrations of acids and alkali	Available testing method		HB		HA			
	Resistance to household chemicals and swimming pool salts	Minimum class B		A					
	Frost resistance	Required		Resistant				ISO 10545-12	
	Dynamic coefficient of friction	See manufacturer's declaration		-		≥ 0,42 wet		ANSI-A326.3	
		See manufacturer's declaration		-		> 0,40		METODO BCRA	
	Shod ramp slipperiness	See manufacturer's declaration		-		R10 (10° < α ≤ 19°)	R11 (19° < α ≤ 27°)	DIN EN 16165 ANNEX B	
	Barefoot ramp slipperiness	See manufacturer's declaration		-		Class B (18° ≤ α < 24°)	Class C (α > 24°)	DIN EN 16165 ANNEX A	
	Pendulum test slipperiness	See manufacturer's declaration		-		PTV > 36 (slider 96)		BS EN 16165 ANNEX C	