## 6 mm / Glazed Porcelain Stoneware

| | E.N. 14411-ISO 13006 . Appendix G. Group BIa. GL | Test method | Reference value | Declared value |
|---|---|---|---|---|
|  | Friction coefficient (slipperiness) | ANSI-A326.3 | - | > 0,42 wet |
|  | Slip resistance with shoes | DIN-EN-16165-ANNEX-B | - | 10° ≤ α < 19° R10 |
|  | Release of hazardous substances | DM-1-2-2007-Reg-CE-1935-2004 | Valore dichiarato per superfici gl con impieghi su piani di lavoro / Declared value for gl surfaces used on worktops / valeur déclarée Pour surfaces gl utilisées sur plans de travail /angegebener wert für Gl oberflächen zum gebrauch als arbeitsplatten / valor declarado Para acabados gl utilizados para superficies de trabajo / заявленное Значение для глазурованных поверхностей, с использованием на рабочих столах | CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / СООТВЕТСТВУЕТ |
|  | Admitted deviation, in %, of the average thickness of each tile from the production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±5% (±0,5 mm) | ± 5% |
|  | Maximum right-angle deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±1,5 mm) | ± 0,2% |
|  | Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±1 mm) | ± 0,15% |
|  | Surface quality | ISO-10545-2 | Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles | CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / СООТВЕТСТВУЕТ |
|  | Flatness (centre curvature / edge curvature / warpage) | ISO-10545-2 | Squadrato ISO 13006 - ±0,4% (±1,8 mm) | ±0,2% |
|  | Maximum straightness deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±0,8 mm) | ± 0,1% |
|  | Amount of water absorbed, in percentage | ISO-10545-3 | E≤0,5% | average value 0,08% |
|  | Bending strength in N/mm2 | ISO-10545-4 | >35 N/mm2 | average value 52 N/mm2 |
|  | Breaking strength in N (thickness < 7,5 mm) | ISO-10545-4 | ≥700 Newton | average value 1350 N |
| | | | Come dichiarato dal produttore / See | Cl. 5 (SHELL / |

| | | | | |
|---|---|---|---|---|
|  | Resistance to abrasion of glazed tiles | ISO-10545-7 | manufacturer’s declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | COTTON) - Cl. 4 (HAZE) - Cl. 3 (GRAPHIT) |
|  | Thermal shock resistance | ISO-10545-9 | Metodo di prova disponibile / Available testing method / Méthode d’essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Glaze crazing resistence | ISO-10545-11 | Richiesta / Required / Requise / Gefordert / Requerida | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Frost resistance | ISO-10545-12 | Richiesta / Required / Requise / Gefordert / Requerida | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Resistance to low concentrations of acids and alkali | ISO-10545-13 | Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | LA |
|  | Resistance to domestic chemicals and additives for swimming pools | ISO-10545-13 | B minimo / B minimum / B minimum / B mindestens / B mínimo | A |
|  | Resistance to staining | ISO-10545-14 | Min Classe 3 | Classe 4 |

**Note:**

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2026 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364

## 9 mm / Glazed Porcelain Stoneware

| | E.N. 14411-ISO 13006 . Appendix G. Group BIa. GL | Test method | Reference value | Declared value |
|---|---|---|---|---|
|  | Friction coefficient (slipperiness) | ANSI-A326.3 | - | > 0,42 wet |
|  | Pendulum friction test | BS-EN-16165-ANNEX-C | - | PTV > 36 wet slider 4S Grip |
|  | Slip resistance with shoes | DIN-EN-16165-ANNEX-B | - | 19° ≤ α < 27° R11 Grip |
|  | Slip resistance with shoes | DIN-EN-16165-ANNEX-B | - | 10° ≤ α < 19° R10 Matte |
|  | Flatness (centre curvature / edge curvature / warpage) | ISO-10545-2 | Squadrato ISO 13006 - ±0,4% (±1,8 mm) | ± 0,35% |
|  | Maximum right-angle deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±1,5 mm) | ± 0,2% |
|  | Length and width: admitted deviation, in %, of the average size of each tile from the production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±1 mm) | ± 0,15% |
|  | Maximum straightness deviation, in %, in relation to the corresponding production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±0,3% (±0,8 mm) | ± 0,1% |
|  | Surface quality | ISO-10545-2 | Il 95% min delle piastrelle deve essere esente da difetti visibili / At least 95% of the tiles must be free from visible flaws / 95% min des carreaux ne doivent présenter aucun défaut visible / Mindestens 95% der Fliesen müssen frei von sichtbaren / mín. el 95% de las baldosas tiene que estar exento de defectos visibles | CONFORME / CONFORMING / CONFORME / KONFORM / CONFORME / СООТВЕТСТВУЕТ |
|  | Admitted deviation, in %, of the average thickness of each tile from the production dimensions | ISO-10545-2 | Squadrato ISO 13006 - ±5% (±0,5 mm) | ± 5% |
|  | Amount of water absorbed, in percentage | ISO-10545-3 | E≤0,5% | average value 0,08% |
|  | Bending strength in N/mm2 | ISO-10545-4 | >35 N/mm2 | average value 50 N/mm2 |
|  | Breaking strength in N (thickness < 7,5 mm) | ISO-10545-4 | ≥1300 Newton | average value 2200 N |
|  | Resistance to abrasion of glazed tiles | ISO-10545-7 | Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | Cl. 5 (SHELL / COTTON) - Cl. 4 (HAZE) - Cl. 2 (GRAPHIT) |

| | | | | |
|---|---|---|---|---|
|  | Thermal shock resistance | ISO-10545-9 | Metodo di prova disponibile / Available testing method / Méthode d’essai disponible / Verfügbare Prüfmethode / Método de ensayo disponible | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Glaze crazing resistence | ISO-10545-11 | Richiesta / Required / Requise / Gefordert / Requerida | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Frost resistance | ISO-10545-12 | Richiesta / Required / Requise / Gefordert / Requerida | RESISTE / RESISTANT / RÉSISTE / ERFÜLLT / RESISTE / УСТОЙЧИВ |
|  | Resistance to low concentrations of acids and alkali | ISO-10545-13 | Come dichiarato dal produttore / See manufacturer's declaration / Selon déclaration du producteur / Entsprechend der Herstellerangaben / Tal como declara el fabricante | LA |
|  | Resistance to domestic chemicals and additives for swimming pools | ISO-10545-13 | B minimo / B minimum / B minimum / B mindestens / B mínimo | A |
|  | Resistance to staining | ISO-10545-14 | Classe 3 min | Cl. 4-5 |

**Note:**

For optimal installation results, Florim recommends maintaining a joint of 2 mm 1/12" for single format installations and 3 mm 1/8" to combine mixed formats.

Copyright © 2026 Florim S.p.A. SB a socio unico.
Sede Legale: Via Canaletto 24, 41042 Fiorano Modenese.
Reg. Imprese di Modena Nr. 01265320364.
Capitale Sociale i.v. Euro 50.000.000 PI/CF 01265320364